

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 044 995 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
18.10.2000 Bulletin 2000/42

(51) Int. Cl.7: **C08F 297/08**, C08L 23/08,
C08F 210/16

(21) Application number: 00100889.5

(22) Date of filing: 28.01.1994

(84) Designated Contracting States:
AT BE DE ES FR GB IT NL PT SE

(30) Priority: 29.01.1993 US 10958

(62) Document number(s) of the earlier application(s) in
accordance with Art. 76 EPC:
94910097.8 / 0 681 592

(71) Applicant:
THE DOW CHEMICAL COMPANY
Midland, Michigan 48640 (US)

(72) Inventors:
• Kolthammer, Brian W.S.
Lake Jackson, TX 77566 (US)

• Cardwell, Robert S.
Lake Jackson, TX 77566 (US)

(74) Representative: Raynor, John
W.H. Beck, Greener & Co
7 Stone Buildings
Lincoln's Inn
London WC2A 3SZ (GB)

Remarks:

This application was filed on 18 - 01 - 2000 as a
divisional application to the application mentioned
under INID code 62.

(54) **Ethylene interpolymerizations**

(57) Processes for polymerizing ethylene/ α -olefin interpolymer compositions are disclosed. The interpolymer compositions have a controlled composition and a controlled molecular weight distribution. The processes utilize a highly-efficient homogeneous catalyst composition in at least one reactor to produce a first interpolymer having a narrow composition distribution and a narrow molecular weight distribution, and a highly-efficient heterogeneous Ziegler catalyst in at least one other reactor. The reactors can be operated sequentially or separately, depending upon the desired product. The novel compositions have good optical properties (e.g., clarity and haze) and good physical properties (e.g., modulus, yield strength, toughness and tear). Useful products which can be formed from these compositions include film, molded articles and fiber.

EP 1 044 995 A1

Description

[0001] This invention relates to ethylene interpolymers and interpolymerization processes. The processes utilize at least one homogeneous polymerization catalyst and at least one heterogeneous polymerization catalyst in separate reactors connected in series or in parallel. Interpolymers produced from such processes are thermoplastic and have surprisingly beneficial properties, including improved impact and tear properties, high modulus and higher crystallization temperatures, and are useful in making molded or shaped articles, film, and the like.

[0002] There are known several polymerization processes for producing polyethylene and ethylene interpolymers, including suspension, gas-phase and solution processes. Of these, the solution process is of commercial significance due to the advantages described in U.S. Pat. 4,330,646 (Sakurai et al.). A most advantageous solution process would be found if the temperature of the polymerization solution could be increased and the properties of the polymers suitably controlled. U.S. Pat. No. 4,314,912 (Lowery et al.) describes a Ziegler-type catalyst suitable for use in high temperature solution polymerization processes. U.S. Pat. No. 4,612,300 (Coleman, III) and USP 4,330,646 describe a catalyst and solution polymerization process for producing polyethylenes having a narrow molecular weight distribution. USP 4,330,646 also describes a process for producing polyethylenes with a broader molecular weight distribution in a solution process. These processes are based on heterogeneous Ziegler type catalysts which produce interpolymers with broad composition distributions regardless of their molecular weight distribution. Such ethylene polymers have deficiencies in some properties, for instance, poor transparency and poor anti-blocking properties.

[0003] Solution polymerization processes for producing ethylene interpolymers with narrow composition distributions are also known. U.S. Pat. No. 4,668,752 (Tominari et al.) describes the production of heterogeneous ethylene copolymers with characteristics which include a narrower composition distribution than conventional heterogeneous copolymers. The utility of such polymer compositions in improving mechanical, optical and other important properties of formed or molded objects is also described. The complex structures of the copolymers necessary to achieve such advantages are finely and difficultly controlled by nuances of catalyst composition and preparation; any drift in which would cause a significant loss in the desired properties. U.S. Pat. No. 3,645,992 (Elston) describes the preparation of homogeneous polymers and interpolymers of ethylene in a solution process operated at temperatures of less than 100°C. These polymers exhibit a "narrow composition distribution", a term defined by a comonomer distribution that within a given polymer molecule and between substantially all molecules of the copolymer is the same. The advantages of such copolymers in improving optical and mechanical properties of objects formed from them is described. These copolymers, however, have relatively low melting points and poor thermal resistance.

[0004] U.S. Pat. No. 4,701,432 (Welborn, Jr.) describes a catalyst composition for the production of ethylene polymers having a varied range of composition distributions and/or molecular weight distributions. Such compositions contain a metallocene and a non-metallocene transition metal compound supported catalyst and an aluminoxane. U.S. Pat. No. 4,659,685 (Coleman, III et al.) describes catalysts which are composed of two supported catalysts (one a metallocene complex supported catalyst and the second a non-metallocene transition metal compound supported catalyst) and an aluminoxane. The disadvantages of such catalysts in the commercial manufacture of ethylene polymers are primarily twofold. Although, the choice of the metallocene and a non-metallocene transition metal compounds and their ratio would lead to polymers of controlled molecular structure, the broad range of ethylene polymer structures required to meet all the commercial demands of this polymer family would require a plethora of catalyst compositions and formulations. In particular, the catalyst compositions containing aluminoxanes (which are generally required in high amounts with respect to the transition metal) are unsuitable for higher temperature solution processes as such amount of the aluminum compounds result in low catalyst efficiencies and yield ethylene polymers with low molecular weights and broad molecular weight distributions.

[0005] It would be desirable to provide an economical solution process which would provide ethylene interpolymers with controlled composition and molecular weight distributions. It would be additionally desirable to provide a process for preparing such interpolymers with reduced complexity and greater flexibility in producing a full range of interpolymer compositions in a controllable fashion. It would be particularly desirable to economically produce ethylene interpolymer compositions having improved impact and tear properties, improved optical properties, high modulus and higher thermal stabilities.

[0006] We have now discovered polymerization processes for preparing interpolymer compositions of controlled composition and molecular weight distributions. The processes utilize at least one homogeneous polymerization catalyst and at least one heterogeneous polymerization catalyst in separate reactors connected in series or in parallel.

[0007] The First Process is directed to:

[0008] A process for preparing an ethylene/a-olefin interpolymer composition, characterized by:

(A) reacting by contacting ethylene and at least one other a-olefin under solution polymerization conditions in the presence of a homogeneous catalyst composition containing either no aluminum cocatalyst or only a small amount of aluminum cocatalyst in at least one reactor to produce a solution of a first interpolymer which has a narrow com-

position distribution and a narrow molecular weight distribution.

(B) reacting by contacting ethylene and at least one other α -olefin under solution polymerization conditions and at a higher polymerization reaction temperature than used in step (A) in the presence of a heterogeneous Ziegler catalyst in at least one other reactor to produce a solution of a second interpolymer which has a broad composition distribution and a broad molecular weight distribution, wherein the Ziegler catalyst comprises

- (i) a solid support component derived from a magnesium halide or silica, and
- (ii) a transition metal component represented by the formulas: $\text{TrX}'_{4-q}(\text{OR}^1)_q$, $\text{TrX}'_{4-q}\text{R}^2_q$, VOX'_3 and $\text{VO}(\text{OR}^1)_3$, wherein:

Tr is a Group IVB, VB, or VIB metal,

q is 0 or a number equal to or less than 4,

X' is a halogen, and

R^1 is an alkyl group, aryl group or cycloalkyl group having from 1 to 20 carbon atoms, and

R^2 is an alkyl group, aryl group, aralkyl group, or substituted aralkyl group, and

(C) combining the solution of the first interpolymer with the solution of the second interpolymer to form a high temperature polymer solution comprising the ethylene/ α -olefin interpolymer composition, and

(D) removing the solvent from the polymer solution of step (C) and recovering the ethylene/ α -olefin interpolymer composition.

[0009] These polymerizations are generally carried out under solution conditions to facilitate the intimate mixing of the two polymer-containing streams. The homogeneous catalyst is chosen from those metallocene-type catalysts which are capable of producing ethylene/ α -olefin interpolymers of sufficiently high molecular weight under solution process polymerization conditions (e.g., temperatures greater than or equal to about 100°C). The heterogeneous catalyst is also chosen from those catalysts which are capable of efficiently producing the polymers under high temperature (e.g., temperatures greater than or equal to about 180°C) solution process conditions.

[0010] In addition, there is provided a second process for preparing interpolymer compositions of controlled composition and controlled molecular weight distributions.

[0011] The Second Process is directed to:

[0012] A process for preparing an ethylene/ α -olefin interpolymer composition, characterized by:

(A) polymerizing ethylene and at least one other α -olefin in a solution process under suitable solution polymerization temperatures and pressures in at least one reactor containing a homogeneous catalyst composition containing either no aluminum cocatalyst or only a small amount of aluminum cocatalyst to produce a first interpolymer solution comprising a first interpolymer having a narrow composition distribution and a narrow molecular weight distribution, and

(B) sequentially passing the interpolymer solution of (A) into at least one other reactor containing a heterogeneous Ziegler catalyst, ethylene and at least one other α -olefin under solution polymerization conditions and at a polymerization temperature higher than that used in (A), to form a high temperature polymer solution comprising the ethylene/ α -olefin interpolymer composition, wherein the Ziegler catalyst comprises

- (i) a solid support component derived from a magnesium halide or silica, and

- (ii) a transition metal component represented by the formulas: $\text{TrX}'_{4-q}(\text{OR}^1)_q$, $\text{TrX}'_{4-q}\text{R}^2_q$, VOX'_3 and $\text{VO}(\text{OR}^1)_3$, wherein:

Tr is a Group IVB, VB, or VIB metal,

q is 0 or a number equal to or less than 4,

X' is a halogen, and

R^1 is an alkyl group, aryl group or cycloalkyl group having from 1 to 20 carbon atoms, and

R^2 is an alkyl group, aryl group, aralkyl group, or substituted aralkyl group, and

(C) removing the solvent from the polymer solution of step (B) and recovering the ethylene/ α -olefin interpolymer composition.

[0013] In either process, the homogeneous catalyst composition preferably exhibits a high reactivity ratio and very readily incorporates higher α -olefins.

[0014] The homogeneous catalysts employed in the production of the homogeneous ethylene interpolymer are

desirably derived from monocyclopentadienyl complexes of the Group IV transition metals which contain a pendant bridging group attached to the cyclopentadienyl ring which acts as a bident ligand. Complex derivatives of titanium in the +3 or +4 oxidation state are preferred.

5 [0015] In another aspect of this invention, there are provided novel interpolymers of ethylene and at least one α -olefin, wherein the interpolymers have controlled composition and molecular weight distributions. The interpolymers have improved mechanical, thermal and optical properties and, surprisingly, the polymer compositions obtained by the processes described herein provide superior properties to materials obtained by merely blending the solid polymers obtained from process step (A) or (B) individually, in the First Process listed above.

10 [0016] The novel polymer compositions of the present invention can be ethylene homopolymers or, preferably, interpolymers of ethylene with at least one C_3 - C_{20} α -olefin and/or C_4 - C_{18} diolefins. Interpolymers of ethylene and 1-octene are especially preferred. The term "interpolymer" is used herein to indicate a copolymer, or a terpolymer, or the like. That is, at least one other comonomer is polymerized with ethylene to make the interpolymer.

Detailed Description of the Invention

15 [0017] The homogeneous polymers and interpolymers of the present invention are herein defined as defined in USP 3,645,992 (Elston). Accordingly, homogeneous polymers and interpolymers are those in which the comonomer is randomly distributed within a given interpolymer molecule and wherein substantially all of the interpolymer molecules have the same ethylene/comonomer ratio within that interpolymer, whereas heterogeneous interpolymers are those in which the interpolymer molecules do not have the same ethylene/comonomer ratio.

20 [0018] The term "narrow composition distribution" used herein describes the comonomer distribution for homogeneous interpolymers and means that the homogeneous interpolymers have only a single melting peak and essentially lack a measurable "linear" polymer fraction. The narrow composition distribution homogeneous interpolymers can also be characterized by their SCBDI (Short Chain Branch Distribution Index) or CDBI (Composition Distribution Branch Index). The SCBDI or CDBI is defined as the weight percent of the polymer molecules having a comonomer content within 50 percent of the median total molar comonomer content. The CDBI of a polymer is readily calculated from data obtained from techniques known in the art, such as, for example, temperature rising elution fractionation (abbreviated herein as "TREF") as described, for example, in Wild et al, *Journal of Polymer Science, Poly. Phys. Ed.*, Vol. 20, p. 441 (1982), or in U.S. Patent 4,798,081. The SCBDI or CDBI for the narrow composition distribution homogeneous interpolymers and copolymers of the present invention is preferably greater than 30 percent, especially greater than 50 percent. The narrow composition distribution homogeneous interpolymers and copolymers used in this invention essentially lack a measurable "high density" (i.e., "linear" or homopolymer) fraction as measured by the TREF technique. The homogeneous interpolymers and polymers have a degree of branching less than or equal to 2 methyls/1000 carbons in 15 percent (by weight) or less, preferably less than 10 percent (by weight), and especially less than 5 percent (by weight).

35 [0019] The term "broad composition distribution" used herein describes the comonomer distribution for heterogeneous interpolymers and means that the heterogeneous interpolymers have a "linear" fraction and that the heterogeneous interpolymers have multiple melting peaks (i.e., exhibit at least two distinct melting peaks). The heterogeneous interpolymers and polymers have a degree of branching less than or equal to 2 methyls/1000 carbons in 10 percent (by weight) or more, preferably more than 15 percent (by weight), and especially more than 20 percent (by weight). The heterogeneous interpolymers also have a degree of branching equal to or greater than 25 methyls/1000 carbons in 25 percent or less (by weight), preferably less than 15 percent (by weight), and especially less than 10 percent (by weight).

40 [0020] The homogeneous polymers and interpolymers used to make the novel polymer compositions of the present invention can be ethylene homopolymers or, preferably, interpolymers of ethylene with at least one C_3 - C_{20} α -olefin and/or C_4 - C_{18} diolefins. Homogeneous copolymers of ethylene and propylene, butene-1, hexene-1, 4-methyl-1-pentene and octene-1 are preferred and copolymers of ethylene and 1-octene are especially preferred.

45 [0021] Either, or both, of the homogeneous ethylene polymer and the heterogeneous ethylene polymer can be an ethylene homopolymer. Preferably, however, either the homogeneous ethylene polymer or the heterogeneous ethylene polymer is an ethylene/ α -olefin interpolymer. Ethylene polymer compositions wherein both the homogeneous ethylene polymer and the heterogeneous ethylene polymer are ethylene/ α -olefin interpolymers are especially preferred.

50 [0022] The homogeneous ethylene polymer and the heterogeneous ethylene polymer used in the compositions described herein can each be made separately in different reactors, and subsequently blended together to make the interpolymer compositions of the present invention. Preferably, though, the homogeneous ethylene polymer and the heterogeneous ethylene polymer used in the compositions described herein are made in a multiple reactor scheme, operated either in parallel or in series. In the multiple reactor scheme, at least one of the reactors makes the homogeneous ethylene polymer and at least one of the reactors makes the heterogeneous ethylene polymer. In a preferred mode of operation, the reactors are operated in a series configuration to make most advantage of the high polymerization temperatures allowed by the heterogeneous catalyst. When the reactors are connected in series, the polymeriza-

tion reaction product from step (A) is fed directly (i.e., sequentially) into the reactor(s) for step (B) along with the ethylene/ α -olefin reactants and heterogeneous catalyst and solvent.

[0023] Other unsaturated monomers usefully polymerized according to the present invention include, for example, ethylenically unsaturated monomers, conjugated or nonconjugated dienes, polyenes, etc. Preferred monomers include the C_2 - C_{10} α -olefins especially ethylene, 1-propene, 1-butene, 1-hexene, 4-methyl-1-pentene, and 1-octene. Other preferred monomers include styrene, halo- or alkyl substituted styrenes, vinylbenzocyclobutane, 1,4-hexadiene, cyclopentene, cyclohexene and cyclooctene.

[0024] The density of the ethylene polymer compositions for use in the present invention is measured in accordance with ASTM D-792 and is generally from 0.87 g/cm³ to 0.965 g/cm³, preferably from 0.88 g/cm³ to 0.95 g/cm³, and especially from 0.9 g/cm³ to 0.935 g/cm³. The density of the homogeneous ethylene polymer used to make the ethylene polymer compositions is generally from 0.865 g/cm³ to 0.92 g/cm³, preferably from 0.88 g/cm³ to 0.915 g/cm³, and especially from 0.89 g/cm³ to 0.91 g/cm³. The density of the heterogeneous ethylene polymer used to make the ethylene polymer compositions is generally from 0.9 g/cm³ to 0.965 g/cm³, preferably from 0.9 g/cm³ to 0.95 g/cm³, and especially from 0.915 g/cm³ to 0.935 g/cm³.

[0025] Generally, the amount of the ethylene polymer produced using the homogeneous catalyst and incorporated into the ethylene polymer composition is from 15 percent to 85 percent, by weight of the composition, preferably 25 percent to 75 percent, by weight of the composition.

[0026] The molecular weight of the ethylene polymer compositions for use in the present invention is conveniently indicated using a melt index measurement according to ASTM D-1238, Condition 190 C/2.16 kg (formally known as "Condition (E)" and also known as I₂). Melt index is inversely proportional to the molecular weight of the polymer. Thus, the higher the molecular weight, the lower the melt index, although the relationship is not linear. The melt index for the ethylene polymer compositions used herein is generally from 0.1 grams/10 minutes (g/10 min) to 100 g/10 min, preferably from 0.3 g/10 min to 30 g/10 min, and especially from 0.5 g/10 min to 10 g/10 min.


[0027] Additives such as antioxidants (e.g., hindered phenolics (e.g., Irganox[®] 1010 made by Ciba Geigy Corp.), phosphites (e.g., Irgafos[®] 168 also made by Ciba Geigy Corp.), cling additives (e.g., polyisobutylene (PIB)), antiblock additives, pigments, and the like can also be included in the polyethylene compositions, to the extent that they do not interfere with the enhanced composition properties discovered by Applicants.

The Homogeneous Catalysts

[0028] The homogeneous catalysts used in the invention are based on those monocyclopentadienyl transition metal complexes described in the art as constrained geometry metal complexes. These catalysts are highly efficient, meaning that they are efficient enough such that the catalyst residues left in the polymer do not influence the polymer quality. Typically, less than or equal to 10 ppm of the metal atom (designated herein as "M") is detectable and, when using the appropriate cocatalyst (e.g., one of the aluminoxanes described herein) the detectable aluminum residue is less than or equal to 250 ppm. Suitable constrained geometry catalysts for use herein preferably include constrained geometry catalysts as disclosed in European patent publication 416,815. The monocyclopentadienyl transition metal olefin polymerization catalysts taught in USP 5,026,798 (Canich) are also suitable for use in preparing the polymers of the present invention.

[0029] The foregoing catalysts may be further described as comprising a metal coordination complex comprising a metal of group 4 of the Periodic Table of the Elements and a delocalized π -bonded moiety substituted with a constrain-inducing moiety, said complex having a constrained geometry about the metal atom such that the angle at the metal between the centroid of the delocalized, substituted π -bonded moiety and the center of at least one remaining substituent is less than such angle in a similar complex containing a similar π -bonded moiety lacking in such constrain-inducing substituent, and provided further that for such complexes comprising more than one delocalized, substituted π -bonded moiety, only one thereof for each metal atom of the complex is a cyclic, delocalized, substituted π -bonded moiety. The catalyst further comprises an activating cocatalyst.

[0030] Preferred catalyst complexes correspond to the formula:



wherein:

M is a metal of group 4 of the Periodic Table of the Elements;

Cp* is a cyclopentadienyl or substituted cyclopentadienyl group bound in an h^5 bonding mode to M;


Z is a moiety comprising boron, or a member of group 14 of the Periodic Table of the Elements, and optionally sulfur or oxygen, said moiety having up to 20 non-hydrogen atoms, and optionally Cp* and Z together form a fused ring system;

X independently each occurrence is an anionic ligand group having up to 30 non-hydrogen atoms;

n is 1 or 2; and

Y is an anionic or nonanionic ligand group bonded to Z and M comprising nitrogen, phosphorus, oxygen or sulfur and having up to 20 non-hydrogen atoms, optionally Y and Z together form a fused ring system.

[0031] More preferably still, such complexes correspond to the formula:



wherein:

R* each occurrence is independently selected from the group consisting of hydrogen, alkyl, aryl, and silyl, and combinations thereof having up to 20 non-hydrogen atoms;

X each occurrence independently is selected from the group consisting of hydride, halo, alkyl, aryl, silyl, aryloxy, alkoxy, amide, siloxy and combinations thereof having up to 20 non-hydrogen atoms;


Y is -O-, -S-, -NR*, -PR*, or a neutral two electron donor ligand selected from the group consisting of OR*, SR*, NR*₂ or PR*₂;

M is as previously defined; and

Z is SiR*₂, CR*₂, SiR*₂SiR*₂, CR*₂CR*₂, CR*=CR*, CR*₂SiR*₂, BR*; wherein

R* each occurrence is independently selected from the group consisting of hydrogen, alkyl, aryl, silyl groups having up to 20 non-hydrogen atoms, and mixtures thereof, or two or more R* groups from Y, Z, or both Y and Z form a fused ring system; and n is 1 or 2.

[0032] Most highly preferred complex compounds are amidosilane- or amidoalkanedyl- compounds corresponding to the formula:



15 wherein:

M is titanium, zirconium or hafnium, bound in an h⁵ bonding mode to the cyclopentadienyl group;

20 R' each occurrence is independently selected from the group consisting of hydrogen, alkyl and aryl and combinations thereof having up to 7 carbon atoms, or silyl;

E is silicon or carbon;

25 X independently each occurrence is hydride, halo, alkyl, aryl, aryloxy or alkoxy of up to 10 carbons, or silyl;

m is 1 or 2; and

n is 1 or 2.

30 **[0033]** Examples of the above most highly preferred metal coordination compounds include compounds wherein the R' on the amido group is methyl, ethyl, propyl, butyl, pentyl, hexyl, (including isomers), norbornyl, benzyl, phenyl, etc.; the cyclopentadienyl group is cyclopentadienyl, indenyl, tetrahydroindenyl, fluorenyl, octahydrofluorenyl, etc.; R' on the foregoing cyclopentadienyl groups each occurrence is hydrogen, methyl, ethyl, propyl, butyl, pentyl, hexyl, (including isomers), norbornyl, benzyl, phenyl, etc.; and X is chloro, bromo, iodo, methyl, ethyl, propyl, butyl, pentyl, hexyl, (including isomers), norbornyl, benzyl, phenyl, etc.

35 **[0034]** Specific compounds include: (tert-butylamido) (tetramethyl-h⁵-cyclopentadienyl)-1,2-ethanediylzirconium dichloride, (tertbutylamido)(tetramethyl-h⁵-cyclopentadienyl)-1,2-ethanediyltitanium dichloride, (methylamido) (tetramethyl-h⁵-cyclopentadienyl)-1,2-ethanediylzirconium dichloride, (methylamido)(tetramethyl-h⁵-cyclopentadienyl)-1,2-ethanediyltitanium dichloride, (ethylamido)(tetramethyl-h⁵-cyclopentadienyl)methylenetitanium dichloride, (tertbutylamido)dibenzyl(tetramethyl-h⁵-cyclopentadienyl) silanezirconium dibenzyl, (benzylamido)dimethyl- (tetramethyl-h⁵-cyclopentadienyl)silanezirconium dichloride, (phenylphosphido)dimethyl(tetramethyl-h⁵-cyclopentadienyl)silanezirconium dibenzyl, (tertbutylamido)dimethyl(tetramethyl-h⁵-cyclopentadienyl)silanezirconium dimethyl, and the like.

40 **[0035]** The catalyst compositions are derived from reacting the metal complex compounds with a suitable activating agent or cocatalyst or combination of cocatalysts. Suitable cocatalysts for use herein include polymeric or oligomeric aluminoxanes, especially aluminoxanes soluble in non-aromatic hydrocarbon solvent, as well as inert, compatible, non-coordinating, ion forming compounds; or combinations of polymeric/oligomeric aluminoxanes and inert, compatible, noncoordinating, ion forming compounds. Preferred cocatalysts contain inert, noncoordinating, boron compounds.

45 **[0036]** Ionic active catalyst species which can be used to polymerize the polymers described herein correspond to the formula:

50

55

[0040] More preferably [A]⁻ corresponds to the formula:



5 wherein:

B is boron in a valence state of 3; and


Q independently each occurrence is selected from the Group consisting of hydride, dialkylamido, halide, alkoxide, aryloxy, hydrocarbyl, and substituted-hydrocarbyl radicals of up to 20 carbons with the proviso that in not more than one occurrence is Q halide.

[0041] Illustrative, but not limiting, examples of boron compounds which may be used as a second component in the preparation of the improved catalysts of this invention are trialkyl-substituted ammonium salts such as triethylammonium tetraphenylborate, tripropylammonium tetraphenylborate, tris(n-butyl)ammonium tetraphenylborate, trimethylammonium tetrakis(p-tolyl)borate, tributylammonium tetrakis(pentafluorophenyl)borate, tripropylammonium tetrakis(2,4-dimethylphenyl)borate, tributylammonium tetrakis(3,5-dimethylphenyl)borate, triethylammonium tetrakis(3,5-di-trifluoromethylphenyl)borate and the like. Also suitable are N,N-dialkylanilinium salts such as N,N-dimethylanilinium tetraphenylborate, N,N-diethylanilinium tetraphenylborate, N,N,2,4,6-pentamethylanilinium tetraphenylborate and the like; dialkylammonium salts such as di(isopropyl)ammonium tetrakis(pentafluorophenyl)borate, dicyclohexylammonium tetraphenylborate and the like; and triarylphosphonium salts such as triphenylphosphonium tetraphenylborate, tris(methylphenyl)phosphonium tetrakis(pentafluorophenyl)borate, tris(dimethylphenyl)phosphonium tetraphenylborate and the like.

[0042] Preferred ionic catalysts are those having a limiting charge separated structure corresponding to the formula:

25

30



35

wherein:

M is a metal of group 4 of the Periodic Table of the Elements;

40

Cp* is a cyclopentadienyl or substituted cyclopentadienyl group bound in an h⁵ bonding mode to M;

Z is a moiety comprising boron, or a member of group 14 of the Periodic Table of the Elements, and optionally sulfur or oxygen, said moiety having up to 20 non-hydrogen atoms, and optionally Cp* and Z together form a fused ring system;

45

X independently each occurrence is an anionic ligand group having up to 30 non-hydrogen atoms;


n is 1 or 2; and

50

XA⁻ is ⁻X(B(C₆F₅)₃).

[0043] This class of cationic complexes can also be conveniently prepared by contacting a metal compound corresponding to the formula:

55




wherein:

[0044] Cp^* , M, and n are as previously defined, with tris(pentafluorophenyl)borane cocatalyst under conditions to cause abstraction of X and formation of the anion $\text{X}(\text{B}(\text{C}_6\text{F}_5)_3)$.

[0045] Preferably X in the foregoing ionic catalyst is $\text{C}_1\text{-C}_{10}$ hydrocarbyl, most preferably methyl or benzyl.

[0046] The preceding formula is referred to as the limiting, charge separated structure. However, it is to be understood that, particularly in solid form, the catalyst may not be fully charge separated. That is, the X group may retain a partial covalent bond to the metal atom, M. Thus, the catalysts may be alternately depicted as possessing the formula:



[0047] The catalysts are preferably prepared by contacting the derivative of a Group 4 metal with the tris(pentafluorophenyl)borane in an inert diluent such as an organic liquid. Tris(pentafluorophenyl)borane is a commonly available Lewis acid that may be readily prepared according to known techniques. The compound is disclosed in Marks, et al. *J. Am. Chem. Soc.* 1991, 113, 3623-3625 for use in alkyl abstraction of zirconocenes.

[0048] The homogeneous catalyst can contain either no aluminum cocatalyst or only a small amount (i.e., from 3:1 Al:M ratio to 100:1 Al:M ratio) of aluminum cocatalyst. For example, the cationic complexes used as homogeneous catalysts may be further activated by the use of an additional activator such as an alkylaluminumoxane. Preferred co-activators include methylaluminumoxane, propylaluminumoxane, isobutylaluminumoxane, combinations thereof and the like. So-called modified methylaluminumoxane (MMAO) is also suitable for use as a cocatalyst. One technique for preparing such modified aluminumoxane is disclosed in U.S. Patent 4,960,878 (Crapo et al.). Aluminumoxanes can also be made as disclosed in U.S. Patents Nos. 4,544,762 (Kaminsky et al.); 5,015,749 (Schmidt et al.); 5,041,583 (Sangokoya); 5,041,584 (Crapo et al.); and 5,041,585 (Deavenport et al.).

[0049] The homogeneous catalysts useful for the production of the ethylene interpolymers of narrow composition and molecular weight distribution may also be supported on an inert support. Typically, the support can be any solid, particularly porous supports such as talc or inorganic oxides, or resinous support materials such as a polyolefin. Preferably, the support material is an inorganic oxide in finely divided form.

[0050] Suitable inorganic oxide materials which are desirably employed in accordance with this invention include Group IIA, IIIA, IVA, or IVB metal oxides such as silica, alumina, and silica-alumina and mixtures thereof. Other inorganic oxides that may be employed either alone or in combination with the silica, alumina or silica-alumina are magnesia, titania, zirconia, and the like. Other suitable support materials, however, can be employed, for example, finely divided polyolefins such as finely divided polyethylene.

[0051] The metal oxides generally contain acidic surface hydroxyl groups which will react with the homogeneous catalyst component added to the reaction slurry. Prior to use, the inorganic oxide support is dehydrated, i.e., subjected to a thermal treatment in order to remove water and reduce the concentration of the surface hydroxyl groups. The treatment is carried out in vacuum or while purging with a dry inert gas such as nitrogen at a temperature of 100°C to 1000°C, and preferably, from 300°C to 800°C. Pressure considerations are not critical. The duration of the thermal treat-

ment can be from 1 to 24 hours; however, shorter or longer times can be employed provided equilibrium is established with the surface hydroxyl groups.

The Heterogeneous Catalysts

5

[0052] The heterogeneous catalysts suitable for use in the invention are typical supported, Ziegler-type catalysts which are particularly useful at the high polymerization temperatures of the solution process. Examples of such compositions are those derived from organomagnesium compounds, alkyl halides or aluminum halides or hydrogen chloride, and a transition metal compound. Examples of such catalysts are described in U.S. Pat Nos. 4,314,912 (Lowery, Jr. et al.), 4,547,475 (Glass et al.), and 4,612,300 (Coleman, III).

10

[0053] Particularly suitable organomagnesium compounds include, for example, hydrocarbon soluble dihydrocarbylmagnesium such as the magnesium dialkyls and the magnesium diaryls. Exemplary suitable magnesium dialkyls include particularly n-butyl-sec-butylmagnesium, diisopropylmagnesium, di-n-hexylmagnesium, isopropyl-n-butylmagnesium, ethyl-n-hexylmagnesium, ethyl-n-butylmagnesium, di-n-octylmagnesium and others wherein the alkyl has from

15

1 to 20 carbon atoms. Exemplary suitable magnesium diaryls include diphenylmagnesium, dibenzylmagnesium and ditolylmagnesium. Suitable organomagnesium compounds include alkyl and aryl magnesium alkoxides and aryloxides and aryl and alkyl magnesium halides with the halogen-free organomagnesium compounds being more desirable.

[0054] Among the halide sources which can be employed herein are the active non-metallic halides, metallic halides, and hydrogen chloride.

20

[0055] Suitable non-metallic halides are represented by the formula R^iX wherein R^i is hydrogen or an active monovalent organic radical and X is a halogen. Particularly suitable non-metallic halides include, for example, hydrogen halides and active organic halides such as t-alkyl halides, allyl halides, benzyl halides and other active hydrocarbyl halides wherein hydrocarbyl is as defined hereinbefore. By an active organic halide is meant a hydrocarbyl halide that contains a labile halogen at least as active, i.e., as easily lost to another compound, as the halogen of sec-butyl chloride, preferably as active as t-butyl chloride. In addition to the organic monohalides, it is understood that organic dihalides, trihalides and other polyhalides that are active as defined hereinbefore are also suitably employed. Examples of preferred active non-metallic halides include hydrogen chloride, hydrogen bromide, t-butyl chloride, t-amyl bromide, allyl chloride, benzyl chloride, crotyl chloride, methylvinyl carbonyl chloride, a-phenylethyl bromide, diphenyl methyl chloride and the like. Most preferred are hydrogen chloride, t-butyl chloride, allyl chloride and benzyl chloride.

25

30

[0056] Suitable metallic halides which can be employed herein include those represented by the formula $MR_{Y-a}X_a$ wherein:

M is a metal of Groups IIB, IIIA or IVA of Mendeleev's Periodic Table of Elements,

R is a monovalent organic radical,

35

X is a halogen,

Y has a value corresponding to the valence of M, and

a has a value from 1 to y.

[0057] Preferred metallic halides are aluminum halides of the formula $AlR_{3-a}X_a$ wherein:

40

each R is independently hydrocarbyl as hereinbefore defined such as alkyl,

X is a halogen and

a is a number from 1 to 3.

45

[0058] Most preferred are alkylaluminum halides such as ethylaluminum sesquichloride, diethylaluminum chloride, ethylaluminum dichloride, and diethylaluminum bromide, with ethylaluminum dichloride being especially preferred. Alternatively, a metal halide such as aluminum trichloride or a combination of aluminum trichloride with an alkyl aluminum halide or a trialkyl aluminum compound may be suitably employed.

50

[0059] It is understood that the organic moieties of the aforementioned organomagnesium, e.g., R^* , and the organic moieties of the halide source, e.g., R and R' , are suitably any other organic radical provided that they do not contain functional groups that poison conventional Ziegler catalysts.

[0060] The magnesium halide can be preformed from the organomagnesium compound and the halide source or it can be formed in situ in which instance the catalyst is preferably prepared by mixing in a suitable solvent or reaction medium (1) the organomagnesium component and (2) the halide source, followed by the other catalyst components.

55

[0061] Any of the conventional Ziegler-Natta transition metal compounds can be usefully employed as the transition metal component in preparing the supported catalyst component. Typically, the transition metal component is a compound of a Group IVB, VB, or VIB metal. The transition metal component is generally, represented by the formulas: $TrX'_{4-q}(OR^1)_q$, $TrX'_{4-q}R^2_q$, VOX'_3 and $VO(OR^1)_3$.

Tr is a Group IVB, VB, or VIB metal, preferably a Group IVB or VB metal, preferably titanium, vanadium or zirconium,

q is 0 or a number equal to or less than 4,

X' is a halogen, and

5. R¹ is an alkyl group, aryl group or cycloalkyl group having from 1 to 20 carbon atoms, and
 R² is an alkyl group, aryl group, aralkyl group, substituted aralkyls, and the like. The aryl, aralkyls and substituted aralkyls contain 1 to 20 carbon atoms, preferably 1 to 10 carbon atoms. When the transition metal compound contains a hydrocarbonyl group, R², being an alkyl, cycloalkyl, aryl, or aralkyl group, the hydrocarbonyl group will preferably not contain an H atom in the position beta to the metal carbon bond. Illustrative but non-limiting examples of aralkyl
 10 groups are methyl, neo-pentyl, 2,2-dimethylbutyl, 2,2-dimethylhexyl; aryl groups such as benzyl; cycloalkyl groups such as 1-norbornyl. Mixtures of these transition metal compounds can be employed if desired.

[0062] Illustrative examples of the transition metal compounds include TiCl₄, TiBr₄, Ti(OC₂H₅)₃Cl, Ti(OC₂H₅)Cl₃,
 15 Ti(OC₄H₉)₃Cl, Ti(OC₃H₇)₂Cl₂, Ti(OC₆H₁₃)₂Cl₂, Ti(OC₈H₁₇)₂Br₂, and Ti(OC₁₂H₂₅)Cl₃, Ti(O-i-C₃H₇)₄, and Ti(O-n-C₄H₉)₄.

[0063] Illustrative examples of vanadium compounds include VCl₄, VOCl₃, VO(OC₂H₅)₃, and VO(OC₄H₉)₃.

[0064] Illustrative examples of zirconium compounds include ZrCl₄, ZrCl₃(OC₂H₅), ZrCl₂(OC₂H₅)₂, ZrCl(OC₂H₅)₃,
 Zr(OC₂H₅)₄, ZrCl₃(OC₄H₉), ZrCl₂(OC₄H₉)₂, and ZrCl(OC₄H₉)₃.

[0065] As indicated above, mixtures of the transition metal compounds may be usefully employed, no restriction
 20 being imposed on the number of transition metal compounds which may be contracted with the support. Any halogenide and alkoxide transition metal compound or mixtures thereof can be usefully employed. The previously named transition metal compounds are especially preferred with vanadium tetrachloride, vanadium oxychloride, titanium tetraisopropoxide, titanium tetrabutoxide, and titanium tetrachloride being most preferred.

[0066] Suitable catalyst materials may also be derived from an inert oxide supports and transition metal compounds.
 25 Examples of such compositions suitable for use in the solution polymerization process are described in U. S. Patent No. 5,231,151.

[0067] The inorganic oxide support used in the preparation of the catalyst may be any particulate oxide or mixed
 oxide as previously described which has been thermally or chemically dehydrated such that it is substantially free of adsorbed moisture.

[0068] The specific particle size, surface area, pore volume, and number of surface hydroxyl groups characteristic
 30 of the inorganic oxide are not critical to its utility in the practice of the invention. However, since such characteristics determine the amount of inorganic oxide to be employed in preparing the catalyst compositions, as well as affecting the properties of polymers formed with the aid of the catalyst compositions, these characteristics must frequently be taken into consideration in choosing an inorganic oxide for use in a particular aspect of the invention. In general, optimum
 35 results are usually obtained by the use of inorganic oxides having an average particle size in the range of 1 to 100 microns, preferably 2 to 20 microns; a surface area of 50 to 1,000 square meters per gram, preferably 100 to 400 square meters per gram; and a pore volume of 0.5 to 3.5 cm³ per gram; preferably 0.5 to 2 cm³ per gram.

[0069] In order to further improve catalyst performance, surface modification of the support material may be
 40 desired. Surface modification is accomplished by specifically treating the support material such as silica, alumina or silica-alumina with an organometallic compound having hydrolytic character. More particularly, the surface modifying agents for the support materials comprise the organometallic compounds of the metals of Group IIA and IIIA of the Peri-
 45 odic Table. Most preferably the organometallic compounds are selected from magnesium and aluminum organometallics and especially from magnesium and aluminum alkyls or mixtures thereof represented by the formulas and R¹MgR² and R¹R²AlR³ wherein each of R¹, R² and R³ which may be the same or different are alkyl groups, aryl groups,
 45 cycloalkyl groups, aralkyl groups, alkoxide groups, alkadienyl groups or alkenyl groups. The hydrocarbon groups R¹, R² and R³ can contain between 1 and 20 carbon atoms and preferably from 1 to about 10 carbon atoms.



[0070] The surface modifying action is effected by adding the organometallic compound in a suitable solvent to a
 slurry of the support material. Contact of the organometallic compound in a suitable solvent and the support is main-
 50 tained from 30 to 180 minutes and preferably from 60 to 90 minutes at a temperature in the range of 20° to 100° C. The diluent employed in slurrying the support can be any of the solvents employed in solubilizing the organometallic compound and is preferably the same.

[0071] In order to more readily produce interpolymer compositions of controlled composition and molecular weight
 distribution, the constrained-geometry component catalyst and the Ziegler-type transition metal catalyst component
 should have different reactivity ratios. The reactivity ratio of the homogeneous catalyst may be higher than the reactivity
 55 ratio of the heterogeneous catalyst. In such instances, the contribution of the narrow composition and molecular weight distribution polymer molecules, formed in the first reactor, to the whole interpolymer product would yield improvements in thermal resistance and crystallization behavior of the resin. Preferably, but not limiting, the reactivity ratio of the homogeneous catalyst introduced into the first reactor should be lower than the reactivity ratio of the heterogeneous

catalyst in order to have the most benefit of a simplified process and to produce interpolymers of the most suitable compositions.

[0072] The reactivity ratios of the metallocenes and transition metal components in general are obtained by methods well known such as, for example, as described in "Linear Method for Determining Monomer Reactivity Ratios in Copolymerization", M. Fineman and S. D. Ross, *J. Polymer Science* 5, 259 (1950) or "Copolymerization", F. R. Mayo and C. Walling, *Chem. Rev.* 46, 191 (1950).

[0073] For example, to determine reactivity ratios, the most widely used copolymerization model is based on the following equations:



here M_1 , M_2 refer to monomer molecules and M_1^* or M_2^* refer to a growing polymer chain to which monomer M_1 or M_2 has most recently attached. M_1 is typically ethylene; M_2 is typically an α -olefin comonomer.

[0074] The k_{ij} values are the rate constants for the indicated reactions. In this case, k_{11} represents the rate at which an ethylene unit inserts into a growing polymer chain in which the previously inserted monomer unit was also ethylene. The reactivity rates follows as: $r_1 = k_{11}/k_{12}$ and $r_2 = k_{22}/k_{21}$ wherein k_{11} , k_{12} , k_{22} , and k_{21} are the rate constants for ethylene (1) or comonomer (2) addition to a catalyst site where the last polymerized monomer is ethylene (k_{1X}) or comonomer (2) (k_{2X}). A lower value of r_1 for a particular catalyst translates into the formation of an interpolpolymer of higher comonomer content produced in a fixed reaction environment. In a preferred embodiment of the invention, the reactivity ratio, r_1 , of the homogeneous catalyst is less than half that of the heterogeneous catalyst.

[0075] Therefore, in the desirable practice of the invention, the homogeneous catalyst produces a polymer of higher comonomer content than that of the polymer produced by the heterogeneous in a reaction environment which is low in the concentration of the comonomer. As the contents of the first reactor enter a second reactor, the concentration of the comonomer in the second reactor is reduced. Hence, the reaction environment in which the heterogeneous catalyst forms polymer is such that a polymer containing a lower comonomer content is produced. Under such reaction conditions, the polymer so formed with have a well-defined and narrow composition distribution and narrow molecular weight distribution. The resulting whole interpolpolymer product can be readily controlled by choice of catalysts, comonomers, and reaction temperatures in an economical and reproducible fashion. In addition, simple changes in monomer concentrations and conversions in each reactor allows the manufacture of a broad range of interpolpolymer products.

[0076] The heterogeneous polymers and interpolymers used to make the novel polymer compositions of the present invention can be ethylene homopolymers or, preferably, interpolymers of ethylene with at least one C_3 - C_{20} α -olefin and/or C_4 - C_{18} diolefins. Heterogeneous copolymers of ethylene and 1-octene are especially preferred.

Polymerization

[0077] The polymerization conditions for manufacturing the polymers of the present invention are generally those useful in the solution polymerization process, although the application of the present invention is not limited thereto. Slurry and gas phase polymerization processes are also believed to be useful, provided the proper catalysts and polymerization conditions are employed.

[0078] Multiple reactor polymerization processes are particularly useful in the present invention, such as those disclosed in USP 3,914,342 (Mitchell). The multiple reactors can be operated in series or in parallel, with at least one constrained geometry catalyst employed in one of the reactors and at least one heterogeneous catalyst employed in at least one other reactor. Preferably, the polymerization temperature of the constrained geometry portion of the polymerization is lower than that of the heterogeneous polymerization portion of the reaction.

[0079] According to one embodiment of the present process, the polymers are produced in a continuous process, as opposed to a batch process. Preferably, the polymerization temperature is from 20°C to 250°C, using constrained geometry catalyst technology. In the generally preferred embodiments where a narrow molecular weight distribution polymer (M_w/M_n of from 1.5 to 2.5) having a higher I_{10}/I_2 ratio (e.g., I_{10}/I_2 of at least 7, preferably at least 8, especially at least 9) is desired, the ethylene concentration in the reactor is preferably not more than 8 percent by weight of the reactor contents, especially not more than 4 percent by weight of the reactor contents. Preferably, the polymerization is

performed in a solution polymerization process. Generally, manipulation of I_{10}/I_2 while holding M_w/M_n relatively low for producing the polymers described herein is a function of reactor temperature and/or ethylene concentration. Reduced ethylene concentration and higher temperature generally produce higher I_{10}/I_2 materials.

[0080] Separation of the interpolymer compositions from the high temperature polymer solution can be accomplished by use of devolatilizing apparatus known to those skilled in the art. Examples include USP 5,084,134 (Mattiussi et al.), USP 3,014,702 (Oldershaw et al.), USP 4,808,262 (Aneja et al.), USP 4,564,063 (Tollar), USP 4,421,162 (Tollar) or USP 3,239,197 (Tollar).

Molecular Weight Distribution Determination

[0081] The interpolymer product samples analyzed by gel permeation chromatography (GPC) on a Waters 150C high temperature chromatographic unit equipped with three mixed porosity columns (Polymer Laboratories 10^3 , 10^4 , 10^5 , and 10^6), operating at a system temperature of 140°C . The solvent is 1,2,4-trichlorobenzene, from which 0.3 percent by weight solutions of the samples are prepared for injection. The flow rate is 1.0 milliliters/minute and the injection size is 200 microliters.

[0082] The molecular weight determination is deduced by using narrow molecular weight distribution polystyrene standards (from Polymer Laboratories) in conjunction with their elution volumes. The equivalent polyethylene molecular weights are determined by using appropriate Mark-Houwink coefficients for polyethylene and polystyrene (as described by Williams and Word in Journal of Polymer Science, Polymer Letters, Vol. 6, (621) 1968) to derive the following equation:

$$M_{\text{polyethylene}} = a \cdot (M_{\text{polystyrene}})^b$$

[0083] In this equation, $a = 0.4316$ and $b = 1.0$. Weight average molecular weight, M_w , is calculated in the usual manner according to the following formula: $M_w = R w_i \cdot M_i$, where w_i and M_i are the weight fraction and molecular weight, respectively, of the i th fraction eluting from the GPC column.

[0084] For the interpolymer fractions and whole interpolymers described herein, the term "narrow molecular weight distribution" means that the M_w/M_n of the interpolymer (or fraction) is less than 3, preferably from 2 to 3. The M_w/M_n of the "narrow molecular weight distribution" interpolymer (or fraction) can also be described by the following equation:

[0085] For the interpolymer fractions and whole interpolymers described herein, the term "broad molecular weight distribution" means that the M_w/M_n of the interpolymer (or fraction) is greater than 3, preferably from 3 to 5.

Crystallization Onset Temperature Measurement

[0086] The crystallization onset temperatures of the polyethylene compositions described herein are measured using differential scanning calorimetry (DSC). Each sample to be tested is made into a compression molded plaque according to ASTM D 1928. The plaques are then thinly sliced at room temperature using a Reichert Microtome or a razor blade to obtain samples having a thickness of about 15 micrometers. About 5 milligrams of each sample to be tested is placed in the DSC pan and heated to about 180°C , held at that temperature for 3 minutes to destroy prior heat history, cooled to -50°C at a rate of $10^\circ\text{C}/\text{minute}$ and held at that temperature for 2 minutes. The crystallization onset temperature and the peak temperature are recorded by the DSC as the temperature at which crystallization begins and the temperature at which the sample is as fully crystallized as possible, respectively, during the cooling period from 180°C to -50°C .

[0087] Other useful physical property determinations made on the novel interpolymer compositions described herein include:

[0088] Melt flow ratio (MFR): measured by determining " I_{10} " (according to ASTM D-1238, Condition 190°C/10 kg (formerly known as "Condition (N)")) and dividing the obtained I_{10} by the I_2 . The ratio of these two melt index terms is the melt flow ratio and is designated as I_{10}/I_2 . For the homogeneous portion of the interpolymer composition, the I_{10}/I_2 ratio is generally greater than or equal to 5.63 and preferably from 5.8 to 8.5. For the heterogeneous portion of the interpolymer composition, the I_{10}/I_2 ratio is typically from 6.8 to 9.5. The I_{10}/I_2 ratio for the whole interpolymer compositions is typically from 6.8 to 10.5.

[0089] 2% Secant Modulus: using a method similar to ASTM D 882. except that 4 specimens are used, a 4 (18 cm) inch gauge length is used and the conditioning period is 24 hours;

Clarity: measured by specular transmittance according to ASTM D 1746, except that the samples are conditioned for 24 hours;

Haze: measured according to ASTM D 1003.

Young's modulus, yield strength and elongation, break strength and elongation, and toughness: using a method similar to ASTM D 882, except that 4 specimens are used and are pulled at 20 inches per minute (50 cm/min) using a 2 inch (5 cm) gauge length;

Spencer Impact: using a method similar to ASTM D 3420, procedure "B", except that the maximum capacity is 1600 grams, the values are normalized for sample thickness and the conditioning period has been shortened from 40 hours to 24 hours; and

Tensile Tear: using a method similar to ASTM D 1938, except that 4 specimens are used.

[0090] Useful articles which can be made from such interpolymer compositions include films (e.g., cast film, blown film or extrusion coated types of film), fibers (e.g., staple fibers, melt blown fibers or spunbonded fibers (using, e.g., systems as disclosed in USP 4,340,563, USP 4,663,220, USP 4,668,566, or USP 4,322,027), and gel spun fibers (e.g., the system disclosed in USP 4,413,110)), both woven and nonwoven fabrics (e.g., spunlaced fabrics disclosed in USP 3,485,706) or structures made from such fibers (including, e.g., blends of these fibers with other fibers, e.g., PET or cotton), and molded articles (e.g., blow molded articles, injection molded articles and rotomolded articles).

[0091] Films particularly benefit from such interpolymer compositions. Films and film structures having the novel properties described herein can be made using conventional hot blown film fabrication techniques or other biaxial orientation process such as tenter frames or double bubble processes. Conventional hot blown film processes are described, for example, in The Encyclopedia of Chemical Technology, Kirk-Othmer, Third Edition, John Wiley & Sons, New York, 1981, Vol. 16, pp. 416-417 and Vol. 18, pp. 191-192. Biaxial orientation film manufacturing process such as described in a "double bubble" process as in U.S. Patent 3,456,044 (Pahlke), and the processes described in U.S. Patent 4,865,902 (Golike et al.), U.S. Patent 4,352,849 (Mueller), U.S. Patent 4,820,557 (Warren), U.S. Patent 4,927,708 (Herran et al.), U.S. Patent 4,963,419 (Lustig et al.), and U.S. Patent 4,952,451 (Mueller) can also be used to make novel film structures from the novel interpolymer compositions. Novel property combinations of such films include unexpectedly high machine and cross direction secant modulus, both first and second machine and cross direction yield, dart impact, cross direction tensile, clarity, 20° gloss, 45° gloss, low haze, low blocking force and low coefficient of friction (COF).

[0092] In addition, these interpolymer compositions have better resistance to melt fracture. An apparent shear stress vs. apparent shear rate plot is used to identify the melt fracture phenomena. According to Ramamurthy in Journal of Rheology, 30(2), 337-357, 1986, above a certain critical flow rate, the observed extrudate irregularities may be broadly classified into two main types: surface melt fracture and gross melt fracture.

[0093] Surface melt fracture occurs under apparently steady flow conditions and ranges in detail from loss of specular gloss to the more severe form of "sharkskin". In this disclosure, the onset of surface melt fracture is characterized at the beginning of losing extrudate gloss at which the surface roughness of extrudate can only be detected by 40X magnification. The critical shear rate at onset of surface melt fracture for the substantially linear olefin polymers is at least 50 percent greater than the critical shear rate at the onset of surface melt fracture of a linear olefin polymer having about the same 12 and Mw/Mn.

[0094] Gross melt fracture occurs at unsteady flow conditions and ranges in detail from regular (alternating rough and smooth, helical, etc.) to random distortions. For commercial acceptability, (e.g., in blown film products), surface defects should be minimal, if not absent. The critical shear rate at onset of surface melt fracture (OSMF) and onset of gross melt fracture (OGMF) will be used herein based on the changes of surface roughness and configurations of the extrudates extruded by a GER.

Example 1

Homogeneous Catalyst Preparation

[0095] A known weight of the constrained-geometry organometallic complex $[(\text{CH}_3)_4\text{C}_5]-(\text{CH}_3)_2\text{Si}-\text{N}-(\text{t}-\text{C}_4\text{H}_9)]\text{Ti}(\text{CH}_3)_2$ was dissolved in Isopar E to give a clear solution with a concentration of Ti of 0.005M. A similar solution of the activator complex, tris(perfluorophenyl)borane (0.010M) was also prepared. A catalyst composition of a few mL total volume was prepared by adding 2.0 mL of Isopar E solution of Ti reagent, 2.0 mL of the borane (for B:Ti = 2:1) and 2 mL Isopar E to a 4 oz (100 ml) glass bottle. The solution was mixed for a few minutes and transferred by syringe to a catalyst injection cylinder on the polymerization reactor.

Heterogeneous Catalyst Preparation

[0096] A heterogeneous Ziegler-type catalyst was prepared substantially according to USP 4,612,300 (Ex. P.), by sequentially adding to a volume of Isopar E, a slurry of anhydrous magnesium chloride in Isopar E, a solution of EtAlCl_2 in hexane, and a solution of $\text{Ti}(\text{O}-i\text{Pr})_4$ in Isopar E, to yield a composition containing a magnesium concentration of

0.17M and a ratio of Mg/Al/Ti of 40/12/3. An aliquot of this composition containing 0.064 mmol of Ti which was treated with a dilute solution of Et₃Al to give an active catalyst with a final Al/Ti ratio of 8/1. This slurry was then transferred to a syringe until it was required for injection into the polymerization reactor.

5 Polymerization

[0097] The polymerization described in this example demonstrates a process for the use of two catalysts, employed sequentially, in two polymerization reactors. A stirred, one-gallon (3.79L) autoclave reactor is charged with 2.1 L of Iso-par™ E (made by Exxon Chemical) and 388 mL of 1-octene comonomer and the contents are heated to 150°C. The reactor is next charged with ethylene sufficient to bring the total pressure to 450 psig (3.2 MPa). A solution containing 0.010 mmol of the active organometallic catalyst described in the catalyst preparation section is injected into the reactor using a high pressure nitrogen sweep. The reactor temperature and pressure are maintained constant at the desired final pressure and temperature by continually feeding ethylene during the polymerization run and cooling the reactor as necessary. After a 10 minute reaction time, the ethylene is shut off and the reactor is depressured to 100 psig (0.8 MPa). Hydrogen is admitted to the reactor and the contents heated. A slurry of the heterogeneous catalyst containing 0.0064 mmol Ti prepared as described in the catalyst preparation section is injected into the reactor using a high pressure nitrogen sweep. The reactor is then continually fed ethylene at 450 psig (3.2 MPa) and the reaction temperature quickly rose to 185°C where the polymerization is sustained for an additional 10 minutes. At this time the reactor is depressured and the hot polymer-containing solution transferred into a nitrogen-purged resin kettle containing 0.2 g Irganox 1010 antioxidant as a stabilizer. After removal of all the solvent in vacuo, the sample is then weighed (yield 270 g) to determine catalyst efficiencies (344300 g PE/ g Ti).

Examples 2 and 3

[0098] Examples 2 and 3 are carried out as in Example 1 except using the catalyst amounts and reactor temperatures described in Table 1. The overall catalyst efficiencies are also shown in the Table.

[0099] The polymer products of Examples 1-3 are tested for various structural, physical and mechanical properties and the results are given in Tables 2, 2A and 2B. Comparative Example A is Attane® 4001 polyethylene and comparative example B is Attane® 4003. Both comparative examples are made by The Dow Chemical Company and are commercial ethyleneoctene copolymers produced under solution process conditions using a typical commercial Ziegler-type catalyst. The data show the polymers of the invention have more narrow molecular weight distributions (M_w/M_n), higher melting points, better crystallization properties (i.e., higher crystallization onset temperatures) and, surprisingly, higher modulus than the commercial comparative examples A and B. The polymers of the invention surprisingly also show better optical properties (i.e., higher clarity and lower haze) than the comparative polymers, even though the polymers have about the same density. In addition, the polymers of the invention show better strength, toughness, tear and impact properties.

Table 1

Process Conditions for Reactor #1 for Examples 1-3				
Ex.	Monomer Volume (ml)	Reactor #1 Temp. (°C)	H ₂ (Reactor #1) (mmol)	Catalyst #1 (micromoles)
1	300	154	0	10
2	300	141	0	5
3	300	134	0	4

Table 1A

Process Conditions for Reactor #2 for Examples 1-3					
Ex.	Monomer Volume (ml)	Reactor #2 Temp. (°C)	H ₂ (Reactor #2) (mmol)	Catalyst #2 (micro-moles)	Overall Titanium Efficiency (g PE/g Ti)
1	300	185	100	6.4	344300
2	300	191	100	9	410100
3	300	193	100	9	425600

Table 2

Examples 1-3 and Comparative Examples A and B						
Ex.	Density (g/cm ³)	Melt Index (I ₂) (g/10 min)	MFR (I ₁₀ /I ₂)	M _w	M _n	MWD (M _w /M _n)
A	0.9136	1.06	8.33	122500	32500	3.77
B	0.9067	0.79	8.81	135300	31900	4.25
1	0.9112	1.07	7.4	115400	40000	2.89
2	0.9071	1.23	7.32	117600	40300	2.92
3	0.9062	1.08	7.46	124500	40100	3.1

Table 2A

Ex.	Melting Temp. (°C)	Crystl. Onset Temp. (°C)	2% Secant Modulus	Young's Modulus (psi)	Clarity (specular trans.)	Haze (%)
A	121	105	20389	20425	0.85	67
B	121	105	13535	13541	1.32	56
1	124	111	25634	25696	2.7	65
2	123	111	28144	28333	5.5	62
3	223	111	28650	28736	3.7	61

Table 2B

Ex.	Yield Strength (psi)	Yield Elongation (%)	Break Strength (psi)	Break Elongation (%)	Toughness (ft.-lb.)	Spencer Impact (psi)	Tensile Strength (g/mil)
A	1370	22	3133	693	1003	847	265
B	1108	24	2450	667	793	688	215
1	1541	16	4134	642	1155	897	311
2	1717	16	5070	658	1327	908	290

Table 2B (continued)

Ex.	Yield Strength (psi)	Yield Elongation (%)	Break Strength (psi)	Break Elongation (%)	Toughness (ft.-lb.)	Spencer Impact (psi)	Tensile Strength (g/mil)
3	1756	15	4679	637	1234	903	311

Example 4**Homogeneous Catalyst Preparation**

[0100] A known weight of the constrained-geometry organometallic complex $\{[(CH_3)_4C_5]-(CH_3)_2Si-N-(t-C_4H_9)]Ti(CH_3)_2\}$ is dissolved in Isopar E to give a clear solution with a concentration of Ti of 0.001M. A similar solution of the activator complex, tris(perfluorophenyl)borane (0.002M) is also prepared. A catalyst composition of a few mL total volume is prepared by adding 1.5 mL of Isopar E solution of Ti reagent, 1.5 mL of the borane (for B:Ti = 2:1) and 2 mL of a heptane solution of methylaluminoxane (obtained commercially from Texas Alkyls as MMAO Type 3A) containing 0.015 mmol Al to a 4 oz (100 ml) glass bottle. The solution is mixed for a few minutes and transferred by syringe to a catalyst injection cylinder on the polymerization reactor.

Heterogeneous Catalyst Preparation

[0101] A heterogeneous Ziegler-type catalyst is prepared similarly to that in Ex. 1 to give an active catalyst containing 0.009 mmol Ti and a final Al/Ti ratio of 8/1. This slurry is then transferred to a syringe in preparation for addition to the catalyst injection cylinder on the polymerization reactor.

Polymerization

[0102] A stirred, one-gallon (3.79L) autoclave reactor is charged with 2.1 L of Isopar™ E (made by Exxon Chemical) and 168 mL of 1-octene comonomer and the contents are heated to 120°C. The reactor is next charged with hydrogen and then with ethylene sufficient to bring the total pressure to 450 psig (3.2MPa). A solution containing 0.0015 mmol of the active organometallic catalyst described in the catalyst preparation section is injected into the reactor using a high pressure nitrogen sweep. The reactor temperature and pressure are maintained at the initial run conditions. After a 10 minute reaction time, the ethylene is shut off and the reactor is depressured to 100 psig (0.8MPa). At this time, an additional 168 mL of 1-octene is added to the reactor along with additional hydrogen and the contents heated. A slurry of the heterogeneous catalyst containing 0.009 mmol Ti prepared as described in the catalyst preparation section is injected into the reactor using a high pressure nitrogen sweep. The reactor is then continually fed ethylene at 450 psig (3.2MPa) and the reaction temperature quickly rises to 189°C where the polymerization is sustained for an additional 10 minutes. At this time the reactor is depressured and the hot polymer-containing solution transferred into a nitrogen-purged resin kettle containing 0.2 g Irganox™ 1010 (a hindered phenolic antioxidant made by Ciba Geigy Corp.) as a stabilizer. After removal of all the solvent in vacuo, the sample is then weighed (yield 202 g) to determine catalyst efficiencies (401630 g PE/g Ti).

Examples 5-7

[0103] Examples 5-7 are carried out as in Example 4 except using the catalysts described in Example 1 and the catalyst amounts and reactor conditions described in Tables 3 and 3A. The overall catalyst efficiencies are also shown in Tables 3 and 3A.

[0104] These examples show that the reaction conditions can be readily controlled to vary the composition and molecular weight distribution of the polymer through a simple change in catalyst amounts and monomer concentrations. Table 4 shows that the interpolymers produced in these examples have a broader molecular weight distribution than those of the earlier examples demonstrating a unique feature of the process control. The physical and mechanical properties still show surprising enhancements over typical commercial copolymers of comparable molecular weight and composition, particularly in strength, impact and tear properties. Comparing examples 4 and 5 with comparative example A (as well as by comparing examples 6 and 7 with comparative example B) shows that the crystallization properties of the polymers of the invention are largely unaffected by broadening the M_w/M_n .

Table 3

Process Conditions for Reactor #1 for Examples 4-7					
Ex.	Monomer Volume (ml)	Reactor #1 Temp. (°C)	Reactor #1 H ₂	Catalyst #1 (micro-moles)	Overall Titanium Efficiency (gPE/gTi)
4	150+150	123	10	1.5	401630
5	150+150	139	50	5	422670
6	300+150	122	0	4	337241
7	300+150	133	100	6	434933

Table 3A

Process Conditions for Reactor #2 for Examples 4-7					
Ex.	Monomer Volume (ml)	Reactor #2 Temp. (°C)	Reactor #2 H ₂ (mmol)	Catalyst #2 (micro-moles)	Overall Titanium Efficiency (g PE/g Ti)
4	150+150	189	300	9	401630
5	150+150	194	50	7.2	422670
6	300+150	189	400	9	337241
7	300+150	188	50	7.2	434933

Table 4

Interpolymer Properties						
Ex.	Density (g/cm ³)	Melt Index (I ₂) (g/10 min)	MFR (I ₁₀ /I ₂)	M _w	M _n	MWD (M _w /M _n)
A	0.9136	1.06	8.33	122500	32500	3.77
4	0.913	1.12	7.45	117900	29400	4.003
5	0.9136	1.17	8.07	135000	42100	3.209
B	0.9067	0.79	8.81	135300	31900	4.25
6	0.9108	3.3	7.4	89700	28700	3.122
7	0.9081	1.53	10.17	125700	31000	4.057

Table 4A

Ex.	Melting peak (°C)	Cryst. Onset Temp. (°C)	Young's Modulus (psi)	2% Secant Modulus	Clarity (specular trans.)	Haze (%)
A	121	105	20425	20389	0.85	67

Table 4A (continued)

Ex.	Melting peak (°C)	Cryst. Onset Temp. (°C)	Young's Modulus (psi)	2% Secant Modulus	Clarity (specular trans.)	Haze (%)
4	123	110	20333	20292	4.7	72
5	123	110	22648	22609	2.32	72
B	121	105	13541	13535	1.32	56
6	124	112	20100	20074	1.15	72
7	123	112	19836	19800	1.85	67

Table 4B

Ex.	Yield strength (psi)	Yield elongation (%)	Break strength (psi)	Break elongation (%)	Toughness (ft-lbs)	Spencer Impact (psi)	Tensile Tear (g/mil)
A	1370	22	3133	693	1003	847	265
4	1468	19	3412	671	1012	977	271
5	1659	16	3608	738	1224	994	313
B	1108	24	2450	667	793	688	215
6	1354	16	2737	670	885	1022	255
7	1326	21	2353	729	914	821	238

Example 8Homogeneous Catalyst Preparation

[0105] A known weight of the constrained-geometry organometallic complex $[(CH_3)_4C_5]-(CH_3)_2Si-N-(t-C_4H_9)Ti(CH_3)_2$ is dissolved in Isopar E to give a clear solution with a concentration of Ti of 0.001M. A similar solution of the activator complex, tris(perfluorophenyl)borane (0.002M) is also prepared. A catalyst composition of a few mL total volume is prepared by adding 1.5 mL of Isopar E solution of Ti reagent, 1.5 mL of the borane (for B:Ti = 2:1) and 2 mL of a heptane solution of methylaluminoxane (obtained commercially from Texas Alkyls as MMAO) containing 0.015 mmol Al to a 4 oz (100 ml) glass bottle. The solution is mixed for a few minutes and transferred by syringe to a catalyst injection cylinder on the polymerization reactor.

Heterogeneous Catalyst Preparation

[0106] A heterogeneous Ziegler-type catalyst is prepared similarly to that in Ex. 1 to give an active catalyst containing 0.009 mmol Ti and a final Al/Ti ratio of 8/1. This slurry is then transferred to a syringe in preparation for addition to the catalyst injection cylinder on the polymerization reactor.

Polymerization

[0107] The polymerization described in this example demonstrates a process for the use of two catalysts, employed sequentially, in two polymerization reactors. A stirred, one-gallon (3.79L) autoclave reactor is charged with 2.1 L of Iso-par™ E (made by Exxon Chemical) and 168 mL of 1-octene comonomer and the contents are heated to 120°C. The reactor is next charged with hydrogen and then with ethylene sufficient to bring the total pressure to 450 psig (3.2 MPa). A solution containing 0.0015 mmol of the active organometallic catalyst described in the catalyst preparation section is

injected into the reactor using a high pressure nitrogen sweep. The reactor temperature and pressure are maintained at the initial run conditions. After a 10 minute reaction time, the ethylene is shut off and the reactor is depressured to 100 psig (0.8 MPa). At this time, an additional 168 mL of 1-octene is added to the reactor along with additional hydrogen and the contents heated. A slurry of the heterogeneous catalyst containing 0.009 mmol Ti prepared as described in the catalyst preparation section is injected into the reactor using a high pressure nitrogen sweep. The reactor is then continually fed ethylene at 450 psig (3.2MPa) and the reaction temperature quickly rises to 189°C where the polymerization is sustained for an additional 10 minutes. At this time the reactor is depressured and the hot polymer-containing solution transferred into a nitrogen-purged resin kettle containing 0.2 g Irganox™ 1010 (a hindered phenolic antioxidant made by Ciba Geigy Corp.) as a stabilizer. After removal of all the solvent in vacuo, the sample is then weighed (yield 202 g) to determine catalyst efficiencies (401630 g PE/ g Ti).

Examples 9-14

[0108] Examples 9-14 are carried out as in Example 8 except using the catalysts described in Example 1 and the catalyst amounts and reactor conditions described in Tables 5 and 5A. The overall catalyst efficiencies are also shown in the Tables.

[0109] These examples show the ability to readily control the reaction conditions to vary the composition and molecular weight distribution of the polymer through a simple change in catalyst amounts and monomer concentrations. The polymers produced in these Examples show a broader molecular weight distribution than those of the earlier examples showing a unique feature of the process control. The physical and mechanical properties still show surprising enhancements over typical commercial copolymers of comparable molecular weight and composition, particularly in strength, impact and tear properties.

[0110] Comparative Example C is Dowlex® 2045, a commercial ethylene/1-octene copolymer made by The Dow Chemical Company. Comparative Example D is Dowlex® 2047, a commercial LLDPE ethylene/1-octene copolymer made by The Dow Chemical Company.

[0111] The data in Table 6 show that the molecular weight distribution (M_w/M_n) can surprisingly remain relatively low, demonstrating a unique feature of the process control of the invention.

Table 5

Process Conditions for Reactor #1 for Examples 8-14					
Ex	Monomer Volume (ml)	Reactor #1 Temp (°C)	Reactor #1 H ₂ (mmol)	Catalyst #1 (micro-moles)	Overall Titanium Efficiency (g PE/g Ti)
8	155	158	25	12.5	286100
9	155	146	20	7.5	312400
10	155	156	0	7.5	326600
11	205	155	0	10	311900
12	230	149	0	7.5	312400
13	155	152	0	7.5	305300
14	150+150	145	0	7.5	298200

Table 5A

Process Conditions for Reactor #2 for Examples 8-14					
Ex.	Monomer Volume (ml)	Reactor #2 Temp (°C)	Reactor #2 H ₂ (mmol)	Catalyst #2 (micro-moles)	Overall Titanium Efficiency (gPE/gTi)
8	155	190	150	7.2	286100
9	155	170	150	7.2	312400

EP 1 044 995 A1

Table 5A (continued)

Process Conditions for Reactor #2 for Examples 8-14					
Ex.	Monomer Volume (ml)	Reactor #2 Temp (°C)	Reactor #2 H ₂ (mmol)	Catalyst #2 (micro-moles)	Overall Titanium Efficiency (gPE/gTi)
10	155	188	200	7.2	326600
11	205	194	150	7.2	311900
12	230	194	150	7.2	312400
13	155	196	400	7.2	305300
14	150+150	195	150	7.2	298200

Table 6

Ex.	Density (g/cm ³)	Melt index (I ₂) (g/10 min)	MFR (I ₁₀ /I ₂)	M _w	M _n	MWD (M _w /M _n)
C	0.9202	1	ND	110000	27300	4.03
8	0.9257	3.1	6.72	80400	32000	2.5
9	0.9225	1.43	6.89	99400	36800	2.7
10	0.9234	1.57	7.04	100400	35200	2.85
D	0.9171	2.3	ND	85500	22000	3.89
11	0.9158	1.39	7.15	100000	35100	2.85
12	0.916	0.91	7.16	113200	37700	3
13	0.915	0.84	7.94	106900	33300	3.21
14	0.9186	1.09	7.1	106200	36400	2.9

ND = Not Determined

Table 6A

Ex.	Melt. Peak (°C)	Crystal. Onset Temp. (°C)	2% Secant Modulus	Young's Modulus (psi)	Clarity (Specular Trans.)	Haze (%)
C	ND	107	29169	29253	3.55	55
8	123	111	48123	48209	0.15	75
9	124	111	47815	47906	0.72	78
10	124	114	34077	34742	0.15	72
D	ND	ND	26094	26094	1.22	49
11	124	113	26245	26304	0.22	69
12	123	111	35492	35599	0.47	67
13	122	110	26466	26534	1.37	63
14	124	111	34989	35032	0.77	66

ND = Not Determined

Table 6B

Ex.	Yield Strength (psi)	Yield elongation (%)	Break strength (psi)	Break elongation (%)	Toughness (ft-lb)	Spencer Impact (psi)	Tensile Tear (g/mil)
C	1830	13	4395	689	1292	735	316
8	2628	12	3893	620	1335	992	450
9	2403	13	4375	613	1343	753	367
10	2240	13	3619	600	1179	1043	326
D	1600	15	4061	771	1351	716	285
11	1905	15	5079	700	1480	820	334
12	2043	15	5385	610	1404	976	336
13	1818	21	4504	612	1203	977	247
14	1933	16	4755	653	1332	741	283

[0112] In step (B) of the Second Process, the ethylene and α -olefin materials may be present as unreacted materials in the reaction product from step (A) or they can each be added to the polymerization reaction mixture in step (B) as needed to make the desired interpolmer. In addition, hydrogen or other telogen can be added to the polymerization mixture of step (B) to control molecular weight.

Example 15

[0113] Example 15 is an *in-situ* blend made according to a continuous polymerization process. In particular, ethylene is fed into a first reactor at a rate of 52 lb/hr (24 kg/hr). Prior to introduction into the first reactor, the ethylene is combined with a diluent mixture comprising ISOPAR™ E hydrocarbon (available from Exxon) and 1-octene. With respect to the first reactor, the 1-octene:ethylene ratio is 9.6:1 (mole percent) and the diluent:ethylene ratio is 9.9:1 (weight). A homogenous constrained geometry catalyst and cocatalyst such as are described in Example 8 above and introduced into the first reactor. The catalyst and cocatalyst concentrations in the first reactor are 0.0030 and 0.0113 molar, respectively. The catalyst and cocatalyst flow rates into the first reactor are 0.537 lbs/hr (0.224 kg/hr) and 0.511 lbs/hr (0.232 kg/hr), respectively. The polymerization is conducted at a reaction temperature of 120°C. The polymer of the first reactor is an ethylene/1-octene copolymer and is estimated to have a density of 0.906 g/cm³, a melt flow ratio (I_{10}/I_2) of about 8-10 and a molecular weight distribution (M_w/M_n) of 2.2.

[0114] The reaction product of the first reactor is transferred to a second reactor. The ethylene concentration in the exit stream from the first reactor is less than four percent, indicating the presence of long chain branching as described in U.S. Patent No. 5, 272,236.

[0115] Ethylene is further fed into a second reactor at a rate of 58 lbs/hr (26 kg/hr). Prior to introduction into the second reactor, the ethylene and a stream of hydrogen are combined with a diluent mixture comprising ISOPAR™ E hydrocarbon (available from Exxon) and 1-octene. With respect to the second reactor, the 1-octene:ethylene ratio is 2.9:1 (mole percent), the diluent:ethylene ratio is 2.8 (weight), and the hydrogen:ethylene ratio is 0.106 (mole percent). A heterogeneous Ziegler catalyst and cocatalyst such as are described in Example 1 above are introduced into the second reactor. The catalyst and cocatalyst concentrations in the second reactor are 0.0023 and 0.0221 molar, respectively. The catalyst and cocatalyst flow rates into the second reactor are 1.4 lbs/hr (0.64 kg/hr) and 0.858 lbs/hr (0.39 kg/hr), respectively. The polymerization is conducted at a reaction temperature of 190°C. The polymer of the second reactor is an ethylene/1-octene copolymer and estimated to have a density of 0.944 g/cm³ and a melt index (I_2) of 1.5 g/10 minutes.

[0116] The total composition comprises 43 percent by weight of the polymer of the first reactor and 57 percent by weight of the polymer of the second reactor. The total composition has a melt index (I_2) of 0.53 g/10 minutes, a density of 0.9246 g/cm³, a melt flow ratio (I_{10}/I_2) of 7.83, and a molecular weight distribution (M_w/M_n) of 2.8.

Claims

1. A process for preparing an ethylene/ α -olefin interpolmer composition, characterized by:

(A) reacting by contacting ethylene and at least one other α -olefin under solution polymerization conditions in the presence of a homogeneous catalyst composition containing either no aluminum cocatalyst or only a small amount of aluminum cocatalyst in at least one reactor to produce a solution of a first interpolymer which has a narrow composition distribution and a narrow molecular weight distribution,

(B) reacting by contacting ethylene and at least one other α -olefin under solution polymerization conditions and at a higher polymerization reaction temperature than used in step (A) in the presence of a heterogeneous Ziegler catalyst in at least one other reactor to produce a solution of a second interpolymer which has a broad composition distribution and a broad molecular weight distribution, wherein the Ziegler catalyst comprises

- (i) a solid support component derived from a magnesium halide or silica, and
- (ii) a transition metal component represented by the formulas: $\text{TrX}'_{4-q}(\text{OR}^1)_q$, $\text{TrX}'_{4-q}\text{R}^2_q$, VOX'_3 and $\text{VO}(\text{OR}^1)_3$, wherein:

Tr is a Group IVB, VB, or VIB metal,

q is 0 or a number equal to or less than 4,

X' is a halogen, and

R¹ is an alkyl group, aryl group or cycloalkyl group having from 1 to 20 carbon atoms, and

R² is an alkyl group, aryl group, aralkyl group, or substituted aralkyl group, and

(C) combining the solution of the first interpolymer with the solution of the second interpolymer to form a high temperature polymer solution comprising the ethylene/ α -olefin interpolymer composition, and

(D) removing the solvent from the polymer solution of step (C) and recovering the ethylene/ α -olefin interpolymer composition.

2. The ethylene/ α -olefin interpolymer composition produced by the process of Claim 1.


3. The process of Claim 1 wherein the α -olefin in each of steps (A) and (B) is 1-octene.

4. The ethylene/1-octene interpolymer composition produced by the process of Claim 3.

5. The process of Claim 1 wherein the homogeneous catalyst composition comprises a metal coordination complex comprising a metal of group 4 of the Periodic Table of the Elements and a delocalized π -bonded moiety substituted with a constrain-inducing moiety, said complex having a constrained geometry about the metal atom such that the angle at the metal between the centroid of the delocalized, substituted π -bonded moiety and the center of at least one remaining substituent is less than such angle in a similar complex containing a similar π -bonded moiety lacking in such constrain-inducing substituent, and provided further that for such complexes comprising more than one delocalized, substituted π -bonded moiety, only one thereof for each metal atom of the complex is a cyclic, delocalized, substituted π -bonded moiety.

6. The process of Claim 5 wherein the homogeneous catalyst composition further comprises an activating cocatalyst.

7. The process of Claim 5 wherein the metal coordination complex corresponds to the formula:



wherein:

M is a metal of group 4 of the Periodic Table of the Elements;

Cp* is a cyclopentadienyl or substituted cyclopentadienyl group bound in an η^5 bonding mode to M;


Z is a moiety comprising boron, or a member of group 14 of the Periodic Table of the Elements, and optionally sulfur or oxygen, said moiety having up to 20 non-hydrogen atoms, and optionally Cp* and Z together form a fused ring system;

5 X independently each occurrence is an anionic ligand group having up to 30 non-hydrogen atoms;

n is 1 or 2; and

10 Y is an anionic or nonanionic ligand group bonded to Z and M comprising nitrogen, phosphorus, oxygen or sulfur and having up to 20 non-hydrogen atoms, optionally Y and Z together form a fused ring system.

8. The process of Claim 5 wherein the metal coordination complex corresponds to the formula:



25

wherein:

R' each occurrence is independently selected from the group consisting of hydrogen, alkyl, aryl, and silyl, and combinations thereof having up to 20 non-hydrogen atoms;

30

X each occurrence independently is selected from the group consisting of hydride, halo, alkyl, aryl, silyl, aryloxy, alkoxy, amide, siloxy and combinations thereof having up to 20 non-hydrogen atoms;

35

Y is -O-, -S-, -NR*, -PR*, or a neutral two electron donor ligand selected from the group consisting of OR*, SR*, NR*₂ or PR*₂;

M is as previously defined; and

40


Z is SiR*₂, CR*₂, SiR*₂SiR*₂, CR*₂CR*₂, CR*=CR*, CR*₂SiR*₂, BR*; wherein

R* each occurrence is independently selected from the group consisting of hydrogen, alkyl, aryl, silyl, halogenated alkyl, halogenated aryl groups having up to 20 non-hydrogen atoms, and mixtures thereof, or two or more R* groups from Y, Z, or both Y and Z form a fused ring system; and n is 1 or 2.

45 9. The process of Claim 5 wherein the metal coordination complex is an amidosilane- or amidoalkanediy- compound corresponding to the formula:

50

55



wherein:

M is titanium, zirconium or hafnium, bound in an h^5 bonding mode to the cyclopentadienyl group;

R' each occurrence is independently selected from the group consisting of hydrogen, alkyl and aryl and combinations thereof having up to 7 carbon atoms, or silyl;


E is silicon or carbon;

X independently each occurrence is hydride, halo, alkyl, aryl, aryloxy or alkoxy of up to 10 carbons, or silyl;

m is 1 or 2; and

n is 1 or 2.

10. The process of Claim 5 wherein the metal coordination complex is an ionic catalyst having a limiting charge separated structure corresponding to the formula:



wherein:

M is a metal of group 4 of the Periodic Table of the Elements;

Cp* is a cyclopentadienyl or substituted cyclopentadienyl group bound in an h^5 bonding mode to M;

Z is a moiety comprising boron, or a member of group 14 of the Periodic Table of the Elements, and optionally sulfur or oxygen, said moiety having up to 20 non-hydrogen atoms, and optionally Cp* and Z together form a fused ring system;

X independently each occurrence is an anionic ligand group having up to 30 non-hydrogen atoms;

n is 1 or 2; and

XA^{*-} is $X(B(C_6F_5)_3)$.

11. The process of Claim 1 wherein the homogeneous catalyst composition has a reactivity ratio less than half that of the heterogeneous catalyst.

12. A process for preparing an ethylene/a-olefin interpolmer composition, characterized by:

(A) polymerizing ethylene and at least one other a-olefin in a solution process under suitable solution polymerization temperatures and pressures in at least one reactor containing a homogeneous catalyst composition containing either no aluminum cocatalyst or only a small amount of aluminum cocatalyst to produce a first interpolmer solution comprising a first interpolmer having a narrow composition distribution and a narrow molecular weight distribution, and

(B) sequentially passing the interpolmer solution of (A) into at least one other reactor containing a heterogeneous Ziegler catalyst, ethylene and at least one other a-olefin under solution polymerization conditions and at a polymerization temperature higher than that used in (A), to form a high temperature polymer solution comprising the ethylene/a-olefin interpolmer composition, wherein the Ziegler catalyst comprises

- (i) a solid support component derived from a magnesium halide or silica, and
- (ii) a transition metal component represented by the formulas: $\text{TrX}'_{4-q}(\text{OR}^1)_q$, $\text{TrX}'_{4-q}\text{R}^2_q$, VOX'_3 and $\text{VO}(\text{OR}^1)_3$, wherein:

Tr is a Group IVB, VB, or VIB metal,

q is 0 or a number equal to or less than 4,

X' is a halogen, and

R¹ is an alkyl group, aryl group or cycloalkyl group having from 1 to 20 carbon atoms, and

R² is an alkyl group, aryl group, aralkyl group, or substituted aralkyl group, and

(C) removing the solvent from the polymer solution of step (B) and recovering the ethylene/a-olefin interpolmer composition.

13. The ethylene/a-olefin interpolmer composition produced by the process of Claim 12.


14. The process of Claim 12 wherein the a-olefin is 1-octene.

15. The ethylene/1-octene interpolmer composition produced by the process of Claim 14.

16. The process of Claim 12 wherein the homogeneous catalyst composition comprises a metal coordination complex comprising a metal of group 4 of the Periodic Table of the Elements and a delocalized π -bonded moiety substituted with a constrain-inducing moiety, said complex having a constrained geometry about the metal atom such that the angle at the metal between the centroid of the delocalized, substituted π -bonded moiety and the center of at least one remaining substituent is less than such angle in a similar complex containing a similar π -bonded moiety lacking in such constrain-inducing substituent, and provided further that for such complexes comprising more than one delocalized, substituted π -bonded moiety, only one thereof for each metal atom of the complex is a cyclic, delocalized, substituted π -bonded moiety.

17. The process of Claim 12 wherein the homogeneous catalyst composition further comprises an activating cocatalyst.

18. The process of Claim 16 wherein the metal coordination complex corresponds to the formula:



wherein:

M is a metal of group 4 of the Periodic Table of the Elements;

Cp* is a cyclopentadienyl or substituted cyclopentadienyl group bound in an h^5 bonding mode to M;


5 Z is a moiety comprising boron, or a member of group 14 of the Periodic Table of the Elements, and optionally sulfur or oxygen, said moiety having up to 20 non-hydrogen atoms, and optionally Cp* and Z together form a fused ring system;

10 X independently each occurrence is an anionic ligand group having up to 30 non-hydrogen atoms;

n is 1 or 2; and

15 Y is an anionic or nonanionic ligand group bonded to Z and M comprising nitrogen, phosphorus, oxygen or sulfur and having up to 20 non-hydrogen atoms, optionally Y and Z together form a fused ring system.

19. The process of Claim 16 wherein the metal coordination complex corresponds to the formula:



30

wherein:

35 R' each occurrence is independently selected from the group consisting of hydrogen, alkyl, aryl, and silyl, and combinations thereof having up to 20 non-hydrogen atoms;

X each occurrence independently is selected from the group consisting of hydride, halo, alkyl, aryl, silyl, aryloxy, alkoxy, amide, siloxy and combinations thereof having up to 20 non-hydrogen atoms;

40 Y is -O-, -S-, -NR*, -PR*, or a neutral two electron donor ligand selected from the group consisting of OR*, SR*, NR*₂ or PR*₂;


M is as previously defined; and

45 Z is SiR*₂, CR*₂, SiR*₂SiR*₂, CR*₂CR*₂, CR*=CR*, CR*₂SiR*₂, BR*; wherein

R* each occurrence is independently selected from the group consisting of hydrogen, alkyl, aryl, silyl, halogenated alkyl, halogenated aryl groups having up to 20 non-hydrogen atoms, and mixtures thereof, or two or more R* groups from Y, Z, or both Y and Z form a fused ring system; and n is 1 or 2.

50 20. The process of Claim 16 wherein the metal coordination complex is an amidosilane- or amidoalkanediyl- compound corresponding to the formula:

55



wherein:

M is titanium, zirconium or hafnium, bound in an h^5 bonding mode to the cyclopentadienyl group;

R' each occurrence is independently selected from the group consisting of hydrogen, alkyl and aryl and combinations thereof having up to 7 carbon atoms, or silyl;


E is silicon or carbon;

X independently each occurrence is hydride, halo, alkyl, aryl, aryloxy or alkoxy of up to 10 carbons, or silyl;

m is 1 or 2; and

n is 1 or 2.

21. The process of Claim 16 wherein the metal coordination complex is an ionic catalyst having a limiting charge separated structure corresponding to the formula:



wherein:

M is a metal of group 4 of the Periodic Table of the Elements;

Cp^* is a cyclopentadienyl or substituted cyclopentadienyl group bound in an h^5 bonding mode to M ;

Z is a moiety comprising boron, or a member of group 14 of the Periodic Table of the Elements, and optionally sulfur or oxygen, said moiety having up to 20 non-hydrogen atoms, and optionally Cp^* and Z together form a fused ring system;

X independently each occurrence is an anionic ligand group having up to 30 non-hydrogen atoms;

n is 1 or 2; and

XA^{*-} is $X(B(C_6F_5)_3)$.

22. The process of Claim 12 wherein the homogeneous catalyst composition has a reactivity ratio less than half that of the heterogeneous catalyst.

5

10

15

20

25

30

35

40

45

50

55



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 10 0889

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
P,X	WO 93 08221 A (THE DOW CHEMICAL) 29 April 1993 (1993-04-29) * page 32, line 12 - line 22; claims 1,4,11,19,23,24 *	1-21	C08F297/08 C08L23/08 C08F210/16
D,A	EP 0 416 815 A (THE DOW CHEMICAL) 13 March 1991 (1991-03-13) * claims 1,9 *	5-10, 17-21	
A	WO 87 03610 A (EXXON RESEARCH AND ENGINEERING) 18 June 1987 (1987-06-18) Abstract	1	
A	EP 0 436 399 A (MITSUI PETROCHEMICAL) 10 July 1991 (1991-07-10) * page 2, line 10 - page 3, line 32 *	1	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C08F C08L
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 17 August 2000	Examiner Kaumann, E
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 10 0889

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

17-08-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9308221 A	29-04-1993	US 5272236 A	21-12-1993
		US 5278272 A	11-01-1994
		CA 2120766 A	29-04-1993
		DE 9219090 U	25-09-1997
		DE 9219173 U	25-03-1999
		DE 69220077 D	03-07-1997
		DE 69220077 T	20-11-1997
		DE 69228265 D	04-03-1999
		DE 69228265 T	02-06-1999
		EP 0608369 A	03-08-1994
		EP 0783006 A	09-07-1997
		EP 0899278 A	03-03-1999
		EP 0899279 A	03-03-1999
		ES 2103976 T	01-10-1997
		ES 2127030 T	01-04-1999
		FI 941727 A	31-05-1994
		JP 2963199 B	12-10-1999
		JP 7500622 T	19-01-1995
		US 5380810 A	10-01-1995
		US 5427807 A	27-06-1995
		US 5562958 A	08-10-1996
		US 5395471 A	07-03-1995
		US 5582923 A	10-12-1996
		US 5525695 A	11-06-1996
		US 5674342 A	07-10-1997
		US 5783638 A	21-07-1998
		US 5685128 A	11-11-1997
		US 5591390 A	07-01-1997
		US 5773155 A	30-06-1998
		US 5595705 A	21-01-1997
		US 5852152 A	22-12-1998
		US 5677383 A	14-10-1997
		US 5665800 A	09-09-1997
		US 5972444 A	26-10-1999
		US 6060567 A	09-05-2000
		US 5847053 A	08-12-1998
		US 5863665 A	26-01-1999
		US 5986028 A	16-11-1999
EP 0416815 A	13-03-1991	AT 156827 T	15-08-1997
		AU 645519 B	20-01-1994
		AU 6203990 A	07-03-1991
		BR 9004460 A	10-09-1991
		CA 2024333 A	01-03-1991
		DE 69031255 D	18-09-1997
		DE 69031255 T	05-03-1998

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 10 0889

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

17-08-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0416815 A		DE 774468 T	02-06-1999
		EP 0764653 A	26-03-1997
		EP 0764664 A	26-03-1997
		EP 0764654 A	26-03-1997
		EP 0774468 A	21-05-1997
		EP 0765888 A	02-04-1997
		ES 2106020 T	01-11-1997
		HK 1001918 A	17-07-1998
		HU 209316 B	28-04-1994
		JP 2684154 B	03-12-1997
		JP 7053618 A	28-02-1995
		JP 2623070 B	25-06-1997
		JP 7070223 A	14-03-1995
		JP 2535249 B	18-09-1996
		JP 3163088 A	15-07-1991
		KR 191380 B	15-06-1999
		KR 191226 B	15-06-1999
		KR 181710 B	15-05-1999
		NO 176964 B	20-03-1995
		NO 179043 B	15-04-1996
		NO 301376 B	20-10-1997
		NO 954469 A	01-03-1991
		NZ 235032 A	28-04-1993
		RU 2073018 C	10-02-1997
		US 5703187 A	30-12-1997
		US 6025448 A	15-02-2000
		US 6013819 A	11-01-2000
		US 6075077 A	13-06-2000
		ZA 9006969 A	27-05-1992
		CN 1049849 A, B	13-03-1991
		US 6087447 A	11-07-2000
		US 5872201 A	16-02-1999
		PL 166689 B	30-06-1995
WO 8703610 A	18-06-1987	US 4874820 A	17-10-1989
		AU 593881 B	22-02-1990
		AU 6776987 A	30-06-1987
		BR 8607039 A	23-02-1988
		EP 0230753 A	05-08-1987
		JP 63502191 T	25-08-1988
		KR 9008459 B	22-11-1990
EP 0436399 A	10-07-1991	DE 3682185 A	28-11-1991
		JP 2953522 B	27-09-1999
		JP 3203909 A	05-09-1991
		JP 2953524 B	27-09-1999

EPO FORM P4489

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 10 0889

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

17-08-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0436399 A		JP 3203912 A	05-09-1991
		JP 2837720 B	16-12-1998
		JP 3203905 A	05-09-1991
		AT 133963 T	15-02-1996
		CA 2033364 A,C	30-06-1991
		DE 69025306 D	21-03-1996
		DE 69025306 T	29-08-1996
		DE 69032530 D	03-09-1998
		DE 69032530 T	21-01-1999
		EP 0656373 A	07-06-1995
		ES 2085900 T	16-06-1996
		ES 2120088 T	16-10-1998
		KR 9406217 B	13-07-1994
		US 5145818 A	08-09-1992
